

10/532635

JC12 Rec PCT/PTC 25 APR 2005

EXPRESS MAIL NO. EV127170292US

**APPLICATION
FOR
UNITED STATES LETTERS PATENT**

Applicants: Hans-Ulrich Hummel, Georg Krämer,
and Hans-Rudolf Stössel

Title: GYSPUM-BASED BUILDING MATERIAL

Beverly A. Lyman, Ph.D.
Wood, Herron & Evans, L.L.P.
2700 Carew Tower
441 Vine Street
Cincinnati, Ohio 45202
(513) 241-2324 (voice)
(513) 241-6234 (facsimile)
Ref. No.: VKSW-02

SPECIFICATION

2/20/05

- 1 -

Gypsum-Based Building Material

5 Gypsum-based building boards, for example, sandwich-type plaster boards and gypsum fiber-boards, are employed in dry construction for the preparation of floors, walls and ceilings.

Typical gypsum-based building boards have a core of cured calcium sulfate dihydrate. It is coated with cardboard or non-woven (glass-fiber web). Typical thickness values are 6, 9.5, 12.5, 15 and 20 mm.

10 For different intended applications, there are different optimized boards, for example, boards having an increased moisture stability, boards having an increased fire resistance or a reduced sound transmission property.

Plasters are coats on raw masonry or raw ceilings made of mortar. In interior construction, they often serve as a substrate for further decoration, and on exterior walls, they serve as protection from weathering.

15 There are also a wide variety of interior plasters which may be employed without further decoration, i.e., so-called decorative plasters.

20 It was the object of the present invention to provide building materials having improved properties. Surprisingly, it has been found that gypsum-based building materials which contain from 1 to 25% by weight of zeolites can lead to a reduction of airborne pollutants in interiors. Preferred zeolite contents are at least 5% by weight, more preferably at least 10% by weight, and particularly preferred are the ranges of from 5 to 20% by weight and from 10 to 15% by weight.

The contents are based on the proportion of zeolite in the dried gypsum-containing mass without, for example, cardboard or fibrous content.

According to the invention, it is particularly preferred to employ natural zeolites, i.e., zeolites which are not prepared synthetically (e.g., by reacting SiO_2 -containing and Al_2O_3 -containing substances with alkali hydroxides at temperatures of more than 50 °C in an aqueous phase). Thus, naturally occurring zeolites are those which
5 are exploited from deposits.

Suitable zeolites include, in particular, those which have a mineral phase composition selected from the group consisting of clinoptilolite, heulandite, chabazite, phillipsite, mordenite and mixtures thereof. Astonishingly, the zeolites can be used not only in thermally activated, i.e., thermally dehydrated, but also in native forms.

10 In a particularly preferred embodiment, the zeolites are employed in a native form, i.e., without thermal activation or dehydration.

Astonishingly, activation of the zeolites apparently occurs during the preparation/drying of the products. The dehydration of zeolites can be measured, for example, by thermogravimetric analysis (TGA).

15 Figure 1 shows a TGA diagram for a naturally occurring zeolite. When the temperature is increased, water is released over an extended range of temperatures. The mass of the sample as a function of temperature and the changes of mass (corresponding to the first derivative) are shown.

Figure 2 shows a TGA diagram for a mixture of 90% by weight of stucco and 10%
20 by weight of naturally occurring zeolite. The mixture has been admixed with water and predried at about 40 °C after curing. The amount of water released as found in the TGA analysis corresponds to the amount of water in the gypsum; the water from the zeolite is not found (any longer). The mass of the sample as a function of temperature and the changes of mass (corresponding to the first derivative) are
25 shown.

Nevertheless, such a zeolite shows the activity for the reduction of airborne pollutants as required according to the invention.

The building materials preferably contain zeolites having a grain size of $\leq 200 \mu\text{m}$, preferably smaller than $150 \mu\text{m}$. This can be achieved most simply by fine milling.

Particularly suitable zeolites have d_{50} values of from about 30 to about $90 \mu\text{m}$, more preferably from 40 to $70 \mu\text{m}$.

- 5 The zeolites preferably have an oil number (determined in accordance with DIN 53199) of at most 25 g/100 g of zeolite, preferably at most 10 g/100 g of zeolite.

The materials employed according to the invention preferably contain less than 3% of diatomaceous earth, and the zeolites are not admixed with "antibacterial cations".

- 10 Particularly preferred building materials are, on the one hand, building boards, especially sandwich-type plaster boards or gypsum fiber-boards, or plasters, especially plasters for applying to interior walls, more preferably decorative plasters, because the admission of air is not hindered by further decoration in this case. The plasters preferably contain the gypsum phase as a binder. The boards are coated,
15 preferably with cardboard or glass fiber web. If desired, they are also perforated (so-called "perforated boards").

For a building board, stucco and zeolites, for example, may be mixed, and the finished board freed from excess water in a continuous dryer.

- 20 The gypsum content is preferably at least 30% by weight, more preferably at least 50% by weight, even more preferably 70% by weight or more, respectively calculated on the cured mixture.

- 25 The present invention also relates to the use of the building materials according to the invention for reducing airborne pollutants in interiors. Airborne pollutants which can be successfully removed from the interior air include, for example, formaldehyde, benzene, ammonia and tobacco smoke. Also smells, e.g., fishy smell, can be

reduced, as could be demonstrated experimentally by the degradation of triethylamine.

Surprisingly, the airborne pollutants are not bound to the materials, but degraded/decomposed, so that no saturation of the materials occurs.

- 5 For formaldehyde, the maximum allowable working place concentration (MAK value) is $600 \mu\text{g}/\text{m}^3$. In a room where people smoke, the average formaldehyde content is around $220 \mu\text{g}/\text{m}^3$ for an air-exchange rate of 0.5 changes/hour. The WHO considers a guidance value of $100 \mu\text{g}/\text{m}^3$ for the protection of health. A value to be sought in habitation is about $60 \mu\text{g}/\text{m}^3$.
- 10 The average benzene content in a room where people smoke is about $45 \mu\text{g}/\text{m}^3$ for an air-exchange rate of 0.5 changes/hour. A value to be sought in habitation is $< 10 \mu\text{g}/\text{m}^3$.

By using the building materials according to the invention, correspondingly reduced values can be obtained.

- 15 The invention is further illustrated by the following Example.

Example

- Gypsum-based building boards containing 10% natural zeolites (native, i.e., non-dehydrated) with a grain size of at most $200 \mu\text{m}$ and a d_{50} value of $40 \mu\text{m}$ were laid in a room with a normal climate, resulting in 1.23 m^2 of gypsum board area per
- 20 1 m^3 of room volume. In this room, a respective noxious gas concentration with the noxious gases formaldehyde and benzene and with a noxious gas mixture from cigarette smoke was adjusted by continuously supplying a defined mixture of noxious gases. The air-exchange rate of the respective mixture was 0.5 changes/hour, i.e., the mixture of noxious substances was renewed completely within two hours.
- 25 In the exhausted mixture, the remaining concentration of noxious substances was measured as a gas concentration.

By the contact with the gypsum-based building boards, the major part of the noxious gases was degraded, and a concentration of noxious gases in the system was obtained from a starting value (supplied mixture) to an equilibrium value (exhausted mixture)

- 5 for formaldehyde of $600 \mu\text{g}/\text{m}^3$ to $96 \mu\text{g}/\text{m}^3$;
 $220 \mu\text{g}/\text{m}^3$ to $40 \mu\text{g}/\text{m}^3$;
- for benzene of $45 \mu\text{g}/\text{m}^3$ to $< 10 \mu\text{g}/\text{m}^3$.

- 10 For cigarette smoke, a substantial reduction of offensive smell from the contact of the smoke with the gypsum-based building boards according to the invention was additionally detected by olfactometry.

In the experimental series, it was additionally established that the noxious substances were not deposited in the gypsum-based building board, but reactively converted to harmless compounds.

- 15 Experiments with altered zeolite proportions in the gypsum-based building boards and altered formulations for the gypsum core, for example, with the addition of 5% wood chips, provided similar results.